



GVM TEST HOUSE
AND RESEARCH CENTRE



Report No.: GVM: WPS: 01622-3/05/2022

ULR: TC906122000000593F

Date: 17-05-2022

Page 1 of 1

AMCHEM PRODUCTS PVT. LTD.

98, Ecotech 12, Greater Noida
(West), 201306

TEST REPORT ON DRYTHANE HE 400

Source of sample	:	Sample Submitted by Customer
Condition of sample	:	Satisfactory
Number of samples Tested	:	01 (One Only).
Customer's Reference#	:	Request dated 09.05.2022
Date of Receipt	:	14.05.2022
Lab Reference Number	:	2022/MAY/01622-3
Sample Description #	:	Drythane HE 400
Test Temperature	:	Temp. 23 ± 2°C & 50 ± 5% RH
Period of Test	:	16.05.2022 To 16.05.2022

TEST RESULTS:

S. N.	Test Conducted	Unit	Test Results	Test Method
1	Tensile Strength	N/mm ²	9.43	ASTM D-638 Type IV: 2016
2	Elongation	%	442	ASTM D-638 Type IV: 2016
3	Tear Strength	N/mm	20.1	ASTM D 624: 2020
4	Puncture Resistance	N	348	ASTM E 154: 2008

As furnished by the customer.

- Note: 1. The Results relate only to the samples tested.
2. Report shall not be reproduced, except in full, without the written approval of the lab.
3. Any correction invalidates this report.

For GVM Test House And Research Centre

 **DINESH BURDE**
Authorised Signatory



AN ISO 9001-2015 CERTIFIED

GVM Test House And Research Centre

Lab Add.: #23/24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node, Navi Mumbai-400701 (India),
Email : lab@gvmtesthouse.com Web.: www.gvmtesthouse.com, Mob: 9689891932.

Regd. Off.: 402, Yogesh Apartment CHS, Plot No. 26, Sector - 8A, Airoli, Navi Mumbai - 400708.

|Testing

|Training

|Auditing