



GVM TEST HOUSE
AND RESEARCH CENTRE

23-24, Yashodeep Heights,
Plot No. 14/15, Sector 29C,
Rabale-Ghansoli Node,
Navi Mumbai - 400 701, INDIA.
Phone: +91 93244 69890
Email: lab@gvmtesthouse.com
www.gvmtesthouse.com



TC-9061

TESTING | TRAINING | AUDITING

Report No.: GVM: WPS: 02182-1/09/2022
ULR: TC906122000001302F

Date: 27-09-2022

Page 1 of 1

AMCHEM PRODUCTS PVT. LTD.
98, Ecotech 12, Greater Noida
(West), 201306

TEST REPORT ON DRYTHANE STANDARD

Source of sample	:	Sample Submitted by Customer
Condition of sample	:	Satisfactory
Number of samples Tested	:	01 (One Only)
Customer's Reference#	:	Request dated 27.09.2022
Date of Receipt	:	24.09.2022
Lab Reference Number	:	2022/SEP/02182-1
Sample Description #	:	Drythane Standard
Test Temperature	:	Temp. 23 ± 2°C & 50 ± 5% RH
Period of Test	:	27.09.2022 To 27.09.2022

TEST RESULTS:

S. N.	Test Conducted	Unit	Test Results	Test Method
1	Tensile Strength - Longitudinal	N/mm ²	17.20	ASTM D-638 Type IV: 2016
2	Elongation - Longitudinal	%	135	ASTM D-638 Type IV: 2016
3	Tensile Strength - Transverse	N/mm ²	17.44	ASTM D-638 Type IV: 2016
4	Elongation - Longitudinal	%	147	ASTM D-638 Type IV: 2016
5	Tear Strength	N/mm	61.22	ASTM D 624:2000
6	Puncture Resistance	N	916	ASTM E 154: 2008
7	Shore D Hardness	Nos.	60	ASTM D 2240: 2015

As furnished by the customer.


- Note:
1. The Results relate only to the samples tested.
 2. Report shall not be reproduced, except in full, without the written approval of the lab.
 3. Any correction invalidates this report.

For GVM Test House And Research Centre



DINESH BURDE

[Signature]
Authorised Signatory



Regd. Office:

402, Yogesh Apartment CHS, Plot No. 26, Sector 8A, Airoli, Navi Mumbai - 400 708, INDIA.
GSTIN: 27BPBPB4090Q1ZM



ISO 9001:2015 Certified